



**NFRC 102-2010 THERMAL PERFORMANCE  
TEST REPORT**

**Rendered to:**

**ALL SEASONS DOOR & WINDOW MFG.**

**SERIES/MODEL: A-500 Double Hung Window**

**TYPE: Vertical Slider (Double Hung)**

<b>Summary of Results</b>	
Standardized Thermal Transmittance (U-Factor)	0.48
Unit Size	47-1/4" x 59" (1200 mm x 1499 mm)
Layer 1	DS Clear Annealed
Gap 1	0.72" Gap, Stainless Steel Spacer (SS-S), 90% Argon-Filled*
Layer 2	DS PPG Solarban 60 (e=0.035*, #3) Annealed

Reference must be made to Report No. 97445.01-116-46, dated 02/02/10 for complete test specimen description and data.



**NFRC 102-2010 THERMAL PERFORMANCE TEST REPORT**

Rendered to:

ALL SEASONS DOOR & WINDOW MFG.  
28 Edgeboro Road  
East Brunswick, New Jersey 8816

Report Number: 97445.01-116-46  
Test Date: 01/20/10  
Report Date: 02/02/10  
Expiration Date: 01/20/14

**Test Sample Identification:**

**Series/Model:** A-500 Double Hung Window

**Type:** Vertical Slider (Double Hung)

**Overall Size:** 47-1/4" x 59" (1200 mm x 1499 mm) (Model Size)

**NFRC Standard Size:** 47.2" x 59.1" (1200 mm wide x 1500 mm high)

**Test Sample Submitted by:** Client

**Test Sample Submitted for:** 0

**Test Procedure:** U-factor tests were performed in a Guarded Hot Box in accordance with NFRC 102-2010, *Test Procedure for Measuring the Steady-State Thermal Transmittance of Fenestration Systems*.

**Test Results Summary:**

Standardized U-factor ( $U_{st}$ ): 0.48 Btu/hr·ft<sup>2</sup>·F CTS Method

**Test Sample Description:**

<b>CONSTRUCTION</b>	<b>Frame</b>	<b>Exterior Sash</b>	<b>Interior Sash</b>
Size (in.)	47-1/4" x 59"	43" x 28-7/8"	44-5/8" x 29"
Daylight Opening (in.)	N/A	40-1/8" x 24-7/8"	41-3/4" x 24-3/4"
<b>CORNERS</b>	Coped	Coped	Coped
Fasteners	Screws	Screws	Screws
Sealant	Yes (pads)	No	No
<b>MATERIAL</b>	AU (0.13")* See Note	AU (0.13")* See Note	AU (0.13")* See Note
Color Exterior	Brown	Brown	Brown
Finish Exterior	Paint	Paint	Paint
Color Interior	Brown	Brown	Brown
Finish Interior	Paint	Paint	Paint
<b>GLAZING METHOD</b>	N/A	Interior	Interior

\*Note: Components wrapped in open celled foam, see assembly drawing for location

**Glazing Information:**

<b>Layer 1</b>	DS Clear Annealed
<b>Gap 1</b>	0.72" Gap, Stainless Steel Spacer (SS-S), 90% Argon-Filled*
<b>Layer 2</b>	DS PPG Solarban 60 (e=0.035*, #3) Annealed
<b>Gas Fill Method</b>	Single-Probe Timed*

*\*Stated per Client/Manufacturer*

*N/A Non-Applicable*

*See Description Table Abbreviations*

Test Sample Description: (Continued)

<b>COMPONENTS</b>		
Type	Quantity	Location
<b>WEATHERSTRIP</b>		
Polypile with center fin	2 Rows	Exterior sash stiles, exterior meeting rail, sill
Polypile with center fin	1 Row	Interior sash stiles, top rail jambs, head
Wrapped foam gasket	1 Row	Interior sash stiles, interior meeting rail
Open-cell foam	2 Rows	All stiles, head, jambs
Open-cell foam	1 Row	Exterior meeting rail, bottom rail, sill, exterior frame perimeter
Wrapped foam pad	2	Interior meeting rail
Open-cell foam pad	2	Top rail
<b>HARDWARE</b>		
Spring loaded latch	2	Top and bottom rail
Spring balance	4	Two per jamb
Metal pivot bar	4	Bottom corners of each sash
Metal tilt-latch	4	Top corners of each sash
<b>DRAINAGE</b>		
(1.25" x 0.25") Weepslot with cover	2	Sill
Sloped sill	1	Sill



## Thermal Transmittance (U-factor)

### Measured Test Data

#### Heat Flows

1. Total Measured Input into Metering Box ( $Q_{total}$ )	790.92 Btu/hr
2. Surround Panel Heat Flow ( $Q_{sp}$ )	60.19 Btu/hr
3. Surround Panel Thickness	4.00 inches
4. Surround Panel Conductance	0.0549 Btu/hr·ft <sup>2</sup> ·F
5. Metering Box Wall Heat Flow ( $Q_{mb}$ )	12.90 Btu/hr
6. EMF vs Heat Flow Equation (equivalent information)	0.0389*EMF + -0.003
7. Flanking Loss Heat Flow ( $Q_{fl}$ )	24.32 Btu/hr
8. Net Specimen Heat Loss ( $Q_s$ )	693.50 Btu/hr

#### Areas

1. Test Specimen Projected Area ( $A_s$ )	19.36 ft <sup>2</sup>
2. Test Specimen Interior Total (3-D) Surface Area ( $A_h$ )	24.68 ft <sup>2</sup>
3. Test Specimen Exterior Total (3-D) Surface Area ( $A_c$ )	23.62 ft <sup>2</sup>
4. Metering Box Opening Area ( $A_{mb}$ )	36.47 ft <sup>2</sup>
5. Metering Box Baffle Area ( $A_{b1}$ )	31.16 ft <sup>2</sup>
6. Surround Panel Interior Exposed Area ( $A_{sp}$ )	17.11 ft <sup>2</sup>

#### Test Conditions

1. Average Metering Room Air Temperature ( $t_h$ )	69.80 F
2. Average Cold Side Air Temperature ( $t_c$ )	-0.40 F
3. Average Guard/Environmental Air Temperature	71.25 F
4. Metering Room Average Relative Humidity	11.77 %
5. Measured Cold Side Wind Velocity (Perpendicular Flow)	17.07 mph
6. Measured Static Pressure Difference Across Test Specimen	0.00" ± 0.04"H <sub>2</sub> O

#### Results

1. Thermal Transmittance of Test Specimen ( $U_s$ )	0.51 Btu/hr·ft <sup>2</sup> ·F
2. Standardized Thermal Transmittance of Test Specimen ( $U_{st}$ )	0.48 Btu/hr·ft <sup>2</sup> ·F

## Thermal Transmittance (U-factor)

### Calculated Test Data

#### CTS Method

1. Emittance of Glass ( $\epsilon_i$ )	0.84
2. Warm Side Baffle Emittance ( $\epsilon_{b1}$ )	0.92
3. Equivalent Warm Side Surface Temperature	44.92 F
4. Equivalent Cold Side Surface Temperature	6.33 F
5. Warm Side Baffle Surface Temperature	68.13 F
6. Measured Warm Side Surface Conductance ( $h_h$ )	1.44 Btu/hr·ft <sup>2</sup> ·F
7. Measured Cold Side Surface Conductance ( $h_c$ )	5.32 Btu/hr·ft <sup>2</sup> ·F
8. Test Specimen Thermal Conductance ( $C_s$ )	0.93 Btu/hr·ft <sup>2</sup> ·F
9. Convection Coefficient ( $K_c$ )	0.34 Btu/(hr·ft <sup>2</sup> ·F <sup>1.25</sup> )
10. Radiative Test Specimen Heat Flow ( $Q_{r1}$ )	331.40 Btu/hr
11. Conductive Test Specimen Heat Flow ( $Q_{c1}$ )	362.11 Btu/hr
12. Radiative Heat Flux of Test Specimen ( $q_{r1}$ )	17.12 Btu/hr·ft <sup>2</sup> ·F
13. Convective Heat Flux of Test Specimen ( $q_{c1}$ )	18.70 Btu/hr·ft <sup>2</sup> ·F
14. Standardized Warm Side Surface Conductance ( $h_{sth}$ )	1.25 Btu/hr·ft <sup>2</sup> ·F
15. Standardized Cold Side Surface Conductance ( $h_{stc}$ )	5.28 Btu/hr·ft <sup>2</sup> ·F
16. Standardized Thermal Transmittance ( $U_{st}$ )	0.48 Btu/hr·ft <sup>2</sup> ·F

#### Test Duration

1. The environmental systems were started at 07:05 hours, 01/19/10.
2. The test parameters were considered stable for two consecutive four hour test periods from 09:05 hours, 01/20/10 to 17:05 hours, 01/20/10.
3. The thermal performance test results were derived from 13:05 hours, 01/20/10 to 17:05 hours, 01/20/10.

The reported Standardized Thermal Transmittance ( $U_{st}$ ) was determined using CTS Method, per Section 8.2(A) of NFRC 102.

**Glazing Deflection (in):**

	<b>Exterior Sash</b>	<b>Interior Sash</b>
Edge Gap Width	0.72	0.72
Estimated center gap width upon receipt of specimen in laboratory (after stabilization)	0.72	0.84
Center gap width at laboratory ambient conditions on day of testing	0.72	0.84
Center gap width at test conditions	0.69	0.72

The sample was inspected for the formation of frost or condensation, which may influence the surface temperature measurements. The sample showed no evidence of condensation/frost at the conclusion of the test.

A calibration of the Architectural Testing Inc. 'thermal test chamber' (ICN 000001) in York, Pennsylvania was conducted in April 2009 in accordance with Architectural Testing Inc. calibration procedure.

"This test method does not include procedures to determine the heat flow due to either air movement through the specimen or solar radiation effects. As a consequence, the thermal transmittance results obtained do not reflect performances which may be expected from field installations due to not accounting for solar radiation, air leakage effects, and the thermal bridge effects that may occur due to the specific design and construction of the fenestration system opening. Therefore, it should be recognized that the thermal transmittance results obtained from this test method are for ideal laboratory conditions and should only be used for fenestration product comparisons and as input to thermal performance analyses which also include solar, air leakage and thermal bridge effects."

"Ratings included in this report are for submittal to an NFRC-licensed IA for certification purposes and are not meant to be used for labeling purposes. Only those values identified on a valid Certification Authorization Report (CAR) are to be used for labeling purposes."

The test sample was installed in a vertical orientation, the exterior of the specimen was exposed to the cold side. The direction of heat transfer was from the interior (warm side) to the exterior (cold side) of the specimen.

ANSI/NCSL Z540-2-1997 type B uncertainty for this test was 1.81%.



Detailed drawings, data sheets, representative samples of the test specimens, a copy of this report, or other pertinent project documentation will be retained by Architectural Testing, Inc. until 1/20/2014. At the end of this retention period such materials shall be discarded without notice and the service life of this report by Architectural Testing, Inc. will expire.

Results obtained are tested values and were secured by using the designated test methods. This report does not constitute certification of this product nor an opinion or endorsement by this laboratory. Ratings included in this report are for submittal to an NFRC licensed IA for certification purposes and are not meant to be used for labeling purposes. Only those values identified on a valid Certification Authorization Report (CAR) are to be used for labeling purposes. It is the exclusive property of the client so named herein and relates only to the specimen(s) tested. This report may not be reproduced, except in full, without the written approval of Architectural Testing, Inc.

For ARCHITECTURAL TESTING, INC.


Tested By:



Digitally Signed by: Benjamin W. Green

Benjamin W. Green  
Technician

Reviewed By:



Digitally Signed by: Shon W. Einsig

Shon W. Einsig  
Senior Technician  
Individual-In-Responsible-Charge

BWG:kmm  
97445.01-116-46

Attachments (pages): This report is complete only when all attachments listed are included.

Appendix-A: Description Table Abbreviations (1)

Appendix-B: Drawings (11)



### Revision Log

<u>Rev. #</u>	<u>Date</u>	<u>Page(s)</u>	<u>Revision(s)</u>
.01R0	02/02/10	All	Original Report Issue. Work requested by Yee Chih of All Seasons Door & Window Mfg.

## Appendix A: Description Table Abbreviations

CODE	Frame / Sash Types
AI	Aluminum w/ Vinyl Inserts (Caps)
AL	Aluminum
AP	Aluminum w/ Thermal Breaks - Partial
AS	Aluminum w/ Steel Reinforcement
AT	Aluminum w/ Thermal Breaks - All Members (> 0.21")
AU	Aluminum Thermally Improved - All Members (0.062" - 0.209")
AV	Aluminum / Vinyl Composite
AW	Aluminum-clad Wood
FG	Fiberglass
PA	ABS Plastic w/ All Members Reinforced
PC	ABS Plastic-clad Aluminum
PF	ABS Plastic w/ Foam-filled Insulation
PH	ABS Plastic w/ Horizontal Members Reinforced
PI	ABS Plastic w/ Reinforcement - Interlock
PL	ABS Plastic
PP	ABS Plastic w/ Reinforcement - Partial
PV	ABS Plastic w/ Vertical Members Reinforced
PW	ABS Plastic-clad Wood
ST	Steel
VA	Vinyl w/ All Members Reinforced
VC	Vinyl-clad Aluminum
VF	Vinyl w/ Foam-filled Insulation
VH	Vinyl w/ Horizontal Members Reinforced
VI	Vinyl w/ Reinforcement - Interlock
VP	Vinyl w/ Reinforcement - Partial
VV	Vinyl w/ Vertical Members Reinforced
VW	Vinyl-clad Wood
VY	Vinyl
WA	Aluminum / Wood composite
WD	Wood
WV	Vinyl / Wood composite
WF	Fiberglass/Wood Combination
WC	Composite/Wood Composite (Shaped vinyl/wood composite members)
CW	Copper Clad Wood
CO	Vinyl/Wood Composite Material

DOOR DETAILS	
N	Not Applicable
CODE	Door Type
EM	Embossed
FL	Flush
LF	Full Lite
LH	1/2 - Lite
LQ	1/4 - Lite
LT	3/4 - Lite
RP	Raised Panel
CODE	Skin
AL	Aluminum
FG	Fiberglass
GS	Galvanized Steel
ST	Steel
WD	Wood
VY	Vinyl
CODE	Panel
FG	Fiberglass
PL	Plastic
WP	Wood - Plywood
WS	Wood - Solid
CODE	Sub-Structure
GS	Galvanized Steel
ST	Steel
WD	Wood
VY	Vinyl
CODE	Core Fill
CH	Cellular - Honeycomb
EP	Expanded Polystyrene
PI	Polyisocyanurate
PU	Polyurethane
WP	Wood - Plywood
WS	Wood - Solid
XP	Extruded Polystyrene

CODE	Spacer Types (See sealant)
A1	Aluminum
A2	Aluminum (Thermally-broken)
A3	Aluminum-reinforced Polymer
A4	Aluminum / Wood
A5	Aluminum-reinforced Butyl (Swiggle)
A6	Aluminum / Foam / Aluminum
A7	Aluminum U-shaped
A8	Aluminum-Butyl (Corrugated) (Duraseal)
ER	EPDM Reinforced Butyl
FG	Fiberglass
GL	Glass
OF	Organic Foam
P1	Duralite
PU	Polyurethane Foam
SU	Stainless Steel, U-shaped
CU	Coated Steel, U-shaped (Intercept)
S2	Steel (Thermally-broken)
S3	Steel / Foam / Steel
S5	Steel-reinforced Butyl
S6	Steel U-channel w/ Thermal Cap
SS	Stainless Steel
CS	Coated Steel
TP	Thermo-plastic
WD	Wood
ZE	Elastomeric Silicone Foam
ZF	Silicone Foam
ZS	Silicone / Steel
N	Not Applicable
TS	Thermo-plastic w/ stainless steel substrate

CODE	Tint Codes
AZ	Azurilite
BL	Blue
BZ	Bronze
CL	Clear
EV	Evergreen
GD	Gold
GR	Green
GY	Gray
LE	Low 'e' Coating
OT	Other (use comment field)
RC	Solar or Reflective Coating
RG	Roller Shades between glazing
RS	Silver (reflective coating)
SF	Suspended Polyester Film
SR	Silver
BG	Blinds between the Glazing
DV	Dynamic Glazing-Variable
DY	Dynamic Glazing-NonVariable

CODE	Gap Fill Codes
AIR	Air
AR2	Argon/Krypton Mixture
AR3	Argon / Krypton / Air
ARG	Argon/Air
CO2	Carbon Dioxide
KRY	Krypton/Air
SF6	Sulfur Hexafluoride
XE2	Xenon/Krypton/Air
XE3	Xenon/Argon/Air
XEN	Xenon/Air
N	Not Applicable

CODE	Spacer Sealant
D	Dual Seal Spacer System
S	Single Seal Spacer System

CODE	Grid Description
N	No Muntins
G	Grids between glass
S	Simulated Divided Lites
T	True Muntins

CODE	Grid Size Codes
	Blank for no grids
0.75	Grids < 1"
1.5	Grids >= 1"

CODE	Thermal Breaks
F	Foam
U	Urethane
V	Vinyl
FB	Fiberglass
O	Other
AB	ABS
NE	Neoprene
AI	Air
N	Not Applicable
P	Polvamide